EP2L
EXTENDED LUBE

GEAR OILS
MOTOR OILS
HYDRAULIC OILS
PIPE COATINGS
THREAD SEALANTS
BEARING GREASES
SPECIALTY GREASES
THREAD COMPOUNDS
SUCKER ROD COATINGS
OUTSIDE PRESERVATIVES
WIRELINE GREASE SEALS
CLEANERS & DEGREASERS
PIPE STORAGE COMPOUNDS
RUST & CORROSION INHIBITORS
THREAD LOCKING COMPOUNDS
VALVE LUBRICANTS & SEALANTS
TOOL JOINT & DRILL COLLAR COMPOUNDS

PRODUCT DESCRIPTION

EP2L Extended Lube is a premium, multipurpose grease made with LIQUILON®* for increased lubricity. LIQUILON®* offers the lowest coefficient of friction of any material on the market today. EP2L Extended Lube plates out on the surface allowing easy sliding, thereby using less electricity to run machine and tools. Wheel bearings move easily when EP2L Extended Lube is applied resulting in more miles per gallon. For use on both high and low temperature applications, EP2L Extended Lube is suitable for a variety of applications when mechanical shear resistance is a requirement. It is water resistant and contains inhibitors for protection against rust and oxidation.

BENEFITS

- **Made with LIQUILON®***
- **Excellent EP properties**
- **Excellent anti-wear properties**
- **Excellent stability**
- **Resists water washout**
- **Protects against rust and oxidation**
- **Prevents corrosion Inhibitor**

APPLICATION

EP2L Extended Lube provides lubrication of all wheel bearings, plain bearings, anti-friction bearings, chassis, all types of bearings, gears and couplings. EP2L Extended Lube is also approved for disc brakes.

TYPICAL OBSERVATIONS

Color	Green
Texture	Smooth
Thickener	Aluminum Complex
Density, lb/gal @ 77°F (25°C)	7.55
Specific Gravity, @ 77°F (25°C)	0.904
Dropping Point, ASTM D-566	>500°F (>260°C)
Flash Point, ASTM D-92	425°F (218°C)
Penetration, ASTM D-217 worked @ 77°F (25°C)	290
Base Oil Viscosity cSt @ 40°C	360
Corrosion Preventive Properties, ASTM D-1743 @ 125°F (51°C)	Pass
Water Washout Characteristics, ASTM D-1264 @ 100°F (37°C)	Nil
Evaporation Loss, ASTM D-972 @ 210°F (98°C)	0.44%
Oil Separation, ASTM D-1742 @ 77°F (25°C)	Nil
Oxidation Stability, ASTM D-942, @ 210°F, 72 hrs. PSI Loss	2
Shelf Life (unopened container)	Four years

RELATED PRODUCTS

EP0 Extended Lube
EP0L Extended Lube with LIQUILON®*
EP1 Extended Lube
EP1L Extended Lube with LIQUILON®*
EP2 Extended Lube

© 2021, BALMAR LLC Made in U.S.A.

WARRANTY Because the conditions of use and the supervision of application are beyond our control, we assume no liability for any product failure or other damage beyond the purchase price of the material furnished by us. No agent, representative, or employee of this Company is authorized to change this provision, which relates to all goods delivered, whether sold, delivered as samples, or otherwise. Each user should independently determine the suitability of this product based on their specific application.

Manufactured by
BALMAR LLC
616 WEST PONT DES MOUTON ROAD | LAFAYETTE, LA 70507
Sales Locations:
LAFAYETTE, LA | HOUSTON, TX | LONGVIEW, TX | MIDLAND, TX | OKLAHOMA CITY, OK

*Registered trade name of Oil Center Research, Inc.
The product information and specifications listed in this publication are constantly being updated to keep up with government regulations and technology changes. Please visit our web site, www.oilcenter.com, or contact your Account Representative for the most current information relating to this product.